

SCHEDA TECNICA PRODOTTO

SLAV FOREST – UA015

PARAMETRI	CARATERISTICHE
	EN Plus A1
UMIDITÀ W-% (ISO 18134)	≤ 10 w-%
TEMPERATURA DI FUSIONE DELLE CENERI °C	≤0,5% (a 550 gradi Celsius)
CONTENUTO CENERI W-% (ISO 18122)	< % 0,7
VALORE CALORICO KWh/Kg (ISO 18125)	≥ 4,8
LUNGHEZZA (ISO 17829)	3,15 – 45 mm
DIAMETRO	6 ± 1mm

Packaging: Bag - 15 Kg
Pellets: 70 Bags - 1050 Kg
Full load bin: 22 pallets - 23.100 KG

FOTO SACCHETTO



UA: 15 кг мішок.
Використовувати тільки в
затверджених і відповідних
системах спалювання згідно
з інструкціями виробника і
національними правилами.
Зберігати в
сухих умовах.

ENG: 15 kg bag. Use only in
approved and appropriate
combustion systems according
to manufacturer instructions
and national regulations.
Store in dry conditions.

IT: Sacco da 15 kg. Utilizzare
unicamente in sistemi di
combustione idonei e
certificati, seguendo le
istruzioni del costruttore e
quanto previsto dalla
normativa nazionale.
Conservare in un luogo
asciutto.

DE: 15 kg Sack. Nur zum
Gebrauch in geeigneten und
genehmigten Heizgeräten
entsprechend den
Herstellerangaben und
gesetzlichen Vorgaben.
Trocken lagern.

CONTACTS FOR
COOPERATION:
TM «SLAVFOREST»
Manufacturer: LLC «SLAV
FOREST»
15300, Koriukivka,
Peredzavodska str. 4
Ukraine, Chernihiv region
WWW.SLAVFOREST.COM.UA
Email: slavforest@gmail.com
Tel.: +380674106181
+380505800292
+380663438924
+380952858202
+380667118108

Юрпак




Wood pellets
WWW.SLAVFOREST.COM.UA



UA 015



Wood pellets
fuel pellets



UA 015

15 kg



Wood pellets
WWW.SLAVFOREST.COM.UA



UA 015

- ДЕРЕВНІ ГРАНУЛИ •
- FUEL PELLETS •
- PELLET DI LEGNO •
- HOLZPELLETS •

ЯКІСТЬ ГРАНУЛ ВІДПОВІДАЄ
НАСТУПНИМ ПАРАМЕТРАМ:
PELLETS QUALITY MEETS THE
FOLLOWING REQUIREMENTS:
LA QUALITÀ DEI PELLETS SODDISFA
I SEGUENTI PARAMETRI:
DIE QUALITÄT DER PELLETS ERFÜLLT
FOLGENDE ANFORDERUNGEN:

•	Діаметр Diameter Diametro Durchmesser	± 6 1 mm
—	Довжина (L) Length Lunghezza Länge	3,15 < L ≤ 40 mm
•	Вологість (M) Humidity Umidiità Wassergehalt	≤ 10 w - %
•	Зольність (A) Ash Content Ceneri Aschegehalt	≤ 0,7 w - %
•	Механічна міцність (DU) Mechanical Durability Durabilità meccanica Mechanische Festigkeit	≥ 98,0 w - %
•	Нижча теплотворна здатність Net Calorific Value Potere calorifico inferiore Heizwert Heizwert Hu	≥ 4,6 kWh /kg
•	Називна щільність (BD) Bulk Density Densità apparente Schüttichte	≤ 600 BD ≤ 750 kg/m³



Design by Urpack™

ACCREDITAMENTI



REGISTRAZIONI



CERTIFICATO ENPlus A1



This certificate attests that for the production of

Wood Pellets
Quality class A1

produced by

LLC „SLAV FOREST“
UA-15300 Koryukivka, Predzavodskaya str. 4

at the site

UA-15300 Koryukivka, Soborna str. 241

an initial inspection was carried out and a continuous surveillance is performed regarding the implementation of the requirements of

ENplus®
Quality Certification Scheme For Wood Pellets



by Holzforschung Austria in the respective current version and that the product meets quality class A1.

For the validity of this certificate see www.holzforschung.at.

ENplus® ID: UA 015

Certificate number: HFA-ENplus-0258

Date of first issue: 26.12.2019

Date of issue: 26.12.2019

Valid until: 25.12.2022

DI Monika Steiner
Authorised signatory



Dr. Manfred Brandstätter
Head of Certification Body

 **HOLZFORSCHUNG AUSTRIA - ÖSTERREICHISCHE GESELLSCHAFT FÜR HOLZFÖRSCHUNG** ZVR 850936522
A-1030 Wien, Franz Grill-Straße 7 Tel +43-1/798 26 23-0 Fax +43-1/798 26 23-50
hfa@holzforschung.at www.holzforschung.at

The Price applicable to the Products may be increased if the market price of fuels, materials, raw materials, equipment, labor and other production costs increases beyond the normal price changes as demonstrated by Sanifix Srl or other sources (Price Index at consumption; Producer price index; other price indices as needed; economic and sector data; letters from the manufacturer or supplier reporting the price increase; and any other data that the seller considers relevant) and the parties accept the increase after trading in good faith.